

**In the Claims**

**Claims 1-31, 33, 35, 43, 45, 47, 50, 52 and 54 are canceled.**

**Amend claims 32, 34, 36-42, 44, 46, 48, 49, 51, 53 and 55-90 where indicated.**

---

- Fi
1. (Canceled)
  2. (Canceled)
  3. (Canceled)
  4. (Canceled)
  5. (Canceled)
  6. (Canceled)
  7. (Canceled)
  8. (Canceled)
  9. (Canceled)
  10. (Canceled)
  11. (Canceled)
  12. (Canceled)
  13. (Canceled)
  14. (Canceled)
  15. (Canceled)
  16. (Canceled)
  17. (Canceled)
  18. (Canceled)
  19. (Canceled)
  20. (Canceled)
  21. (Canceled)
  22. (Canceled)
  23. (Canceled)
  24. (Canceled)
  25. (Canceled)
  26. (Canceled)
  27. (Canceled)
  28. (Canceled)
  29. (Canceled)
  30. (Canceled)
  31. (Canceled)

- 1           **32. (Allowed)**     A method of making a magnetic read head, which includes a spin
- 2 valve sensor, comprising the steps of:
- 3           a making of the spin valve sensor comprising the steps of:
- 4                 forming a free layer structure that has a magnetic moment and an easy axis;
- 5                 forming a ferromagnetic pinned layer structure that has a magnetic moment;
- 6                 forming a pinning layer exchange coupled to the pinned layer structure for pinning
- 7 the magnetic moment of the pinned layer structure;
- 8                 forming a nonmagnetic conductive spacer layer between the free layer structure and
- 9 the pinned layer structure;

10 forming the free layer structure by obliquely ion beam sputtering at least one cobalt  
11 or cobalt based layer in the presence of a magnetic field oriented in a direction of said easy  
12 axis; and

13 the oblique ion beam sputtering being at angles  $\alpha = 40^\circ$  and  $\beta = 10^\circ - 30^\circ$ , wherein  
14 angles  $\alpha$  and  $\beta$  form first and second planes respectively which are orthogonal with respect  
15 to one another.

33. (Canceled)

34. (Allowed) A method of making a magnetic read head, which includes a spin  
valve sensor, comprising the steps of:

a making of the spin valve sensor comprising the steps of:

forming a free layer structure that has a magnetic moment and an easy axis;

forming a ferromagnetic pinned layer structure that has a magnetic moment;

forming a pinning layer exchange coupled to the pinned layer structure for pinning  
the magnetic moment of the pinned layer structure;

forming a nonmagnetic conductive spacer layer between the free layer structure and  
the pinned layer structure;

forming the free layer structure by obliquely ion beam sputtering at least one cobalt  
or cobalt based layer in the presence of a magnetic field oriented in a direction of said easy  
axis;

the pinning layer structure being formed by forming a nickel oxide (NiO) layer and  
an alpha iron oxide ( $\alpha$  FeO) layer wherein each of the nickel oxide (NiO) layer and the  
alpha iron oxide ( $\alpha$  FeO) layer has been formed by oblique ion beam sputtering at angles  
 $\alpha$  and  $\beta$  wherein angles  $\alpha$  and  $\beta$  form first and second planes respectively which are  
orthogonal with respect to one another.

35. (Canceled)

36. (Allowed) A method as claimed in claim 32 further comprising the steps of:  
forming the free layer structure with a nickel iron based layer that interfaces the cobalt or  
cobalt based layer; and  
said forming of the cobalt or cobalt based layer so that it interfaces the spacer layer.

1           **37.**   (Allowed)   A method as claimed in claim 36 further comprising the step of:  
2           after said oblique ion beam sputtering in the presence of said field oriented in said  
3           direction of the easy axis, further forming said at least one cobalt or cobalt based layer by  
4           annealing said at least one cobalt or cobalt based layer.

1           **38.**   (Allowed)   A method as claimed in claim 36 wherein said cobalt based layer  
2           is formed of cobalt iron (CoFe).

1           **39.**   (Allowed)   A method as claimed in claim 38 wherein said annealing is at a  
2           temperature from 150°C to 270°C.

1           **40.**   (Allowed)   A method of making a magnetic read head, which includes a spin  
2           valve sensor, comprising the steps of:

3           forming the spin valve sensor as follows:

4           forming a ferromagnetic pinned layer structure that has a magnetic moment;

5           forming a pinning layer exchange coupled to the pinned layer structure for pinning  
6           the magnetic moment of the pinned layer structure;

7           forming a nonmagnetic conductive spacer layer between the free layer structure and  
8           the pinned layer structure; and

9           forming the pinning layer structure of a nickel oxide (NiO) layer and an alpha iron  
10          oxide ( $\alpha$ FeO) layer wherein at least one of the nickel oxide (NiO) layer and the alpha iron  
11          oxide ( $\alpha$ FeO) layer has been obliquely ion beam sputtered at angles  $\alpha$  and  $\beta$  wherein angles  
12           $\alpha$  and  $\beta$  form first and second planes respectively which are orthogonal with respect to one  
13          another.

1           **41.**   (Allowed)   A method of making a magnetic read head, which includes a spin  
2           valve sensor, comprising:

3           a making of the spin valve sensor including the steps of:

4           forming a free layer structure that has a magnetic moment and an easy axis;

5           forming a ferromagnetic pinned layer structure that has a magnetic moment;

6           forming a pinning layer exchange coupled to the pinned layer structure for pinning  
7           the magnetic moment of the pinned layer structure;

8           forming a nonmagnetic conductive spacer layer between the free layer structure and  
9           the pinned layer structure;

10          a making the free layer structure including the steps of:

11 obliquely ion beam sputtering first and second cobalt or cobalt based layers  
12 and a nickel iron based layer in the presence of a magnetic field oriented in a  
13 direction of said easy axis with the first and second cobalt or cobalt based layers  
14 interfacing the spacer layer and a cap layer respectively and the nickel iron based  
15 layer being located between and interfacing the first and second cobalt or cobalt  
16 based layers;

17 the oblique ion beam sputtering being at angles  $\alpha = 40^\circ$  and  $\beta = 10^\circ - 30^\circ$   
18 wherein angles  $\alpha$  and  $\beta$  form first and second planes respectively which are  
19 orthogonal with respect to one another; and

20 after said oblique ion beam sputtering in the presence of said field oriented  
21 in said direction on the easy axis, annealing each of the cobalt or cobalt based  
22 layers and the nickel iron based layer.

Fi  
1  
Const  
2  
4  
5  
42. (Allowed) A method as claimed in claim 41 including:  
forming nonmagnetic nonconductive first and second read gap layers;  
forming the spin valve sensor between the first and second read gap layers;  
forming ferromagnetic first and second shield layers; and  
forming the first and second read gap layers between the first and second shield layers.

43. (Canceled)

1 44. (Allowed) A method as claimed in claim 42 wherein a forming of the pinned  
2 layer structure comprises the steps of:  
3 forming ferromagnetic first and second antiparallel (AP) pinned layers with the first AP  
4 layer interfacing the pinning layer; and  
5 forming an antiparallel (AP) coupling layer between the first and second AP layers.

45. (Canceled)

1 46. (Allowed) A method as claimed in claim 44 wherein the step of oblique ion  
2 beam sputtering includes the steps of:  
3 providing a sputtering chamber;  
4 providing a nonmagnetic conductive target in the sputtering chamber that has a nominal  
5 planar surface;  
6 positioning a substrate in the chamber that has a nominal planar surface at angles  $\alpha$  and  $\beta$   
7 to the nominal planar surface of the target;

8 providing an ion beam gun in the chamber for bombarding the target with ions which  
9 causes ions of the material to be sputtered from the target and deposited on the substrate to form  
10 said cobalt or cobalt based layers; and

11 angle  $\alpha = 40^\circ$  and angle  $\beta = 10^\circ - 30^\circ$  wherein angles  $\alpha$  and  $\beta$  form first and second planes  
12 respectively which are orthogonal with respect to one another and are angles between the nominal  
13 surface planes of the target and the substrate.

47. (Canceled)

FI  
Cont'd  
1 48. (Allowed/Currently Amended) A method of making magnetic head assembly that  
2 includes a write head and a read head, comprising the steps of:

3 a making of the write head including:

4 forming ferromagnetic first and second pole piece layers in pole tip, yoke and back  
5 gap regions wherein the yoke region is located between the pole tip and back gap regions;

6 forming a nonmagnetic nonconductive write gap layer between the first and second  
7 pole piece layers in the pole tip region;

8 forming an insulation stack with at least one coil layer embedded therein between  
9 the first and second pole piece layers in the yoke region; and

10 connecting the first and second pole piece layers at said back gap region; and

11 making the read head as follows:

12 forming a spin valve sensor and first and second nonmagnetic first and second read  
13 gap layers with the spin valve sensor located between the first and second read gap layers;

14 forming a ferromagnetic first shield layer; and

15 forming the first and second read gap layers between the first shield layer and the  
16 first pole piece layer; and

17 a making of the spin valve sensor comprising the steps of:

18 forming a free layer structure that has a magnetic moment and an easy axis;

19 forming a ferromagnetic pinned layer structure that has a magnetic moment;

20 forming a pinning layer exchange coupled to the pinned layer structure for pinning  
21 the magnetic moment of the pinned layer structure;

22 forming a nonmagnetic conductive spacer layer between the free layer structure and  
23 the pinned layer structure;

24 a making of the free layer structure including the step of:

25 obliquely ion beam sputtering first and second cobalt or cobalt based layers  
26 and a nickel iron based layer in the presence of a magnetic field oriented in a  
27 direction of said easy axis with the first and second cobalt or cobalt based layers  
28 interfacing the spacer layer structure and a gap layer respectively and the nickel  
29 iron based layer being located between and interfacing the first and second cobalt  
30 or cobalt based layers;

31 the oblique ion beam sputtering being at angles  $\alpha = 40^\circ$  and  $\beta = 10^\circ - 30^\circ$   
32 wherein angles  $\alpha$  and  $\beta$  form first and second planes respectively which are  
33 orthogonal with respect to one another; and

34 after said oblique ion beam sputtering in the presence of said field oriented  
35 in said direction of the easy axis, annealing each of the cobalt or cobalt based  
36 layers and the nickel iron based layer.

36  
FI.  
1  
Control  
3  
4  
49. (Allowed) A method as described in claim 48 including:

forming a ferromagnetic second shield layer;

forming a nonmagnetic isolation layer between the second shield layer and the first pole  
piece layer.

50. (Canceled)

1 51. (Allowed) A method as claimed in claim 48 wherein a forming of the pinned  
2 layer structure comprises the steps of:

3 forming ferromagnetic first and second antiparallel (AP) pinned layers with the first AP  
4 pinned layer interfacing the pinning layer; and

5 forming an antiparallel (AP) coupling layer located between the first and second AP layers.

52. (Canceled)

1 53. (Allowed) A method as claimed in claim 51 wherein the step of oblique ion  
2 beam sputtering includes the steps of:

3 providing a sputtering chamber;

4 providing a nonmagnetic conductive target in the sputtering chamber that has a nominal  
5 planar surface;

6 positioning a substrate in the chamber that has a nominal planar surface at an angle to the  
7 nominal planar surface of the target;

8 providing an ion beam gun in the chamber for bombarding the target with ions which  
9 causes ions of the material to be sputtered from the target and deposited on the substrate to form  
10 said cobalt or cobalt based layers.

54. (Canceled)

1 55. (Original) A method of making a magnetic layer and/or an antiferromagnetic  
2 (AFM) layer for an electrical device comprising the steps of:  
3 obliquely ion beam sputtering at least one material layer from a target onto a substrate to  
4 form said magnetic layer and/or antiferromagnetic (AFM) layer;  
5 the oblique ion beam sputtering being at angles  $\alpha$  and  $\beta$  wherein each angle  $\alpha$  and  $\beta$  is  
6 acute and wherein the angles  $\alpha$  and  $\beta$  form first and second planes respectively which are  
7 orthogonal with respect to each other.

8  
9  
10  
11  
12  
13  
14  
15  
16  
17  
18  
19  
20  
21  
22  
23  
24  
25  
26  
27  
28  
29  
30  
31  
32  
33  
34  
35  
36  
37  
38  
39  
40  
41  
42  
43  
44  
45  
46  
47  
48  
49  
50  
51  
52  
53  
54  
55  
56  
57  
58  
59  
60  
61  
62  
63  
64  
65  
66  
67  
68  
69  
70  
71  
72  
73  
74  
75  
76  
77  
78  
79  
80  
81  
82  
83  
84  
85  
86  
87  
88  
89  
90  
91  
92  
93  
94  
95  
96  
97  
98  
99  
100  
101  
102  
103  
104  
105  
106  
107  
108  
109  
110  
111  
112  
113  
114  
115  
116  
117  
118  
119  
120  
121  
122  
123  
124  
125  
126  
127  
128  
129  
130  
131  
132  
133  
134  
135  
136  
137  
138  
139  
140  
141  
142  
143  
144  
145  
146  
147  
148  
149  
150  
151  
152  
153  
154  
155  
156  
157  
158  
159  
160  
161  
162  
163  
164  
165  
166  
167  
168  
169  
170  
171  
172  
173  
174  
175  
176  
177  
178  
179  
180  
181  
182  
183  
184  
185  
186  
187  
188  
189  
190  
191  
192  
193  
194  
195  
196  
197  
198  
199  
200  
201  
202  
203  
204  
205  
206  
207  
208  
209  
210  
211  
212  
213  
214  
215  
216  
217  
218  
219  
220  
221  
222  
223  
224  
225  
226  
227  
228  
229  
230  
231  
232  
233  
234  
235  
236  
237  
238  
239  
240  
241  
242  
243  
244  
245  
246  
247  
248  
249  
250  
251  
252  
253  
254  
255  
256  
257  
258  
259  
260  
261  
262  
263  
264  
265  
266  
267  
268  
269  
270  
271  
272  
273  
274  
275  
276  
277  
278  
279  
280  
281  
282  
283  
284  
285  
286  
287  
288  
289  
290  
291  
292  
293  
294  
295  
296  
297  
298  
299  
300  
301  
302  
303  
304  
305  
306  
307  
308  
309  
310  
311  
312  
313  
314  
315  
316  
317  
318  
319  
320  
321  
322  
323  
324  
325  
326  
327  
328  
329  
330  
331  
332  
333  
334  
335  
336  
337  
338  
339  
340  
341  
342  
343  
344  
345  
346  
347  
348  
349  
350  
351  
352  
353  
354  
355  
356  
357  
358  
359  
360  
361  
362  
363  
364  
365  
366  
367  
368  
369  
370  
371  
372  
373  
374  
375  
376  
377  
378  
379  
380  
381  
382  
383  
384  
385  
386  
387  
388  
389  
390  
391  
392  
393  
394  
395  
396  
397  
398  
399  
400  
401  
402  
403  
404  
405  
406  
407  
408  
409  
410  
411  
412  
413  
414  
415  
416  
417  
418  
419  
420  
421  
422  
423  
424  
425  
426  
427  
428  
429  
430  
431  
432  
433  
434  
435  
436  
437  
438  
439  
440  
441  
442  
443  
444  
445  
446  
447  
448  
449  
450  
451  
452  
453  
454  
455  
456  
457  
458  
459  
460  
461  
462  
463  
464  
465  
466  
467  
468  
469  
470  
471  
472  
473  
474  
475  
476  
477  
478  
479  
480  
481  
482  
483  
484  
485  
486  
487  
488  
489  
490  
491  
492  
493  
494  
495  
496  
497  
498  
499  
500  
501  
502  
503  
504  
505  
506  
507  
508  
509  
510  
511  
512  
513  
514  
515  
516  
517  
518  
519  
520  
521  
522  
523  
524  
525  
526  
527  
528  
529  
530  
531  
532  
533  
534  
535  
536  
537  
538  
539  
540  
541  
542  
543  
544  
545  
546  
547  
548  
549  
550  
551  
552  
553  
554  
555  
556  
557  
558  
559  
560  
561  
562  
563  
564  
565  
566  
567  
568  
569  
570  
571  
572  
573  
574  
575  
576  
577  
578  
579  
580  
581  
582  
583  
584  
585  
586  
587  
588  
589  
590  
591  
592  
593  
594  
595  
596  
597  
598  
599  
600  
601  
602  
603  
604  
605  
606  
607  
608  
609  
610  
611  
612  
613  
614  
615  
616  
617  
618  
619  
620  
621  
622  
623  
624  
625  
626  
627  
628  
629  
630  
631  
632  
633  
634  
635  
636  
637  
638  
639  
640  
641  
642  
643  
644  
645  
646  
647  
648  
649  
650  
651  
652  
653  
654  
655  
656  
657  
658  
659  
660  
661  
662  
663  
664  
665  
666  
667  
668  
669  
670  
671  
672  
673  
674  
675  
676  
677  
678  
679  
680  
681  
682  
683  
684  
685  
686  
687  
688  
689  
690  
691  
692  
693  
694  
695  
696  
697  
698  
699  
700  
701  
702  
703  
704  
705  
706  
707  
708  
709  
710  
711  
712  
713  
714  
715  
716  
717  
718  
719  
720  
721  
722  
723  
724  
725  
726  
727  
728  
729  
730  
731  
732  
733  
734  
735  
736  
737  
738  
739  
740  
741  
742  
743  
744  
745  
746  
747  
748  
749  
750  
751  
752  
753  
754  
755  
756  
757  
758  
759  
760  
761  
762  
763  
764  
765  
766  
767  
768  
769  
770  
771  
772  
773  
774  
775  
776  
777  
778  
779  
780  
781  
782  
783  
784  
785  
786  
787  
788  
789  
790  
791  
792  
793  
794  
795  
796  
797  
798  
799  
800  
801  
802  
803  
804  
805  
806  
807  
808  
809  
810  
811  
812  
813  
814  
815  
816  
817  
818  
819  
820  
821  
822  
823  
824  
825  
826  
827  
828  
829  
830  
831  
832  
833  
834  
835  
836  
837  
838  
839  
840  
841  
842  
843  
844  
845  
846  
847  
848  
849  
850  
851  
852  
853  
854  
855  
856  
857  
858  
859  
860  
861  
862  
863  
864  
865  
866  
867  
868  
869  
870  
871  
872  
873  
874  
875  
876  
877  
878  
879  
880  
881  
882  
883  
884  
885  
886  
887  
888  
889  
890  
891  
892  
893  
894  
895  
896  
897  
898  
899  
900  
901  
902  
903  
904  
905  
906  
907  
908  
909  
910  
911  
912  
913  
914  
915  
916  
917  
918  
919  
920  
921  
922  
923  
924  
925  
926  
927  
928  
929  
930  
931  
932  
933  
934  
935  
936  
937  
938  
939  
940  
941  
942  
943  
944  
945  
946  
947  
948  
949  
950  
951  
952  
953  
954  
955  
956  
957  
958  
959  
960  
961  
962  
963  
964  
965  
966  
967  
968  
969  
970  
971  
972  
973  
974  
975  
976  
977  
978  
979  
980  
981  
982  
983  
984  
985  
986  
987  
988  
989  
990  
991  
992  
993  
994  
995  
996  
997  
998  
999  
1000

56. (Currently Amended) A method as claimed in claim 55 wherein A method of making a magnetic layer and/or an antiferromagnetic (AFM) layer for an electrical device comprising the steps of:  
obliquely ion beam sputtering at least one material layer from a target onto a substrate to form said magnetic layer and/or antiferromagnetic (AFM) layer;  
the oblique ion beam sputtering being at angles  $\alpha$  and  $\beta$  wherein each angle  $\alpha$  and  $\beta$  is acute and wherein the angles  $\alpha$  and  $\beta$  form first and second planes respectively which are orthogonal with respect to each other; and  
the angle  $\beta$  is being 10° to 30°.

1 57. (Currently Amended) A method as claimed in claim 55 wherein A method of making a magnetic layer and/or an antiferromagnetic (AFM) layer for an electrical device comprising the steps of:  
2 obliquely ion beam sputtering at least one material layer from a target onto a substrate to form said magnetic layer and/or antiferromagnetic (AFM) layer;  
3 the oblique ion beam sputtering being at angles  $\alpha$  and  $\beta$  wherein each angle  $\alpha$  and  $\beta$  is acute and wherein the angles  $\alpha$  and  $\beta$  form first and second planes respectively which are orthogonal with respect to each other; and  
4 the angle  $\beta$  is being 20° and the angle  $\alpha$  is being 40°.

1           58. (Currently Amended) ~~A method as claimed in claim 55 wherein~~ A method of  
2 making a magnetic layer and/or an antiferromagnetic (AFM) layer for an electrical device  
3 comprising the steps of:

4           obliquely ion beam sputtering at least one material layer from a target onto a substrate to  
5 form said magnetic layer and/or antiferromagnetic (AFM) layer;

6           the oblique ion beam sputtering being at angles  $\alpha$  and  $\beta$  wherein each angle  $\alpha$  and  $\beta$  is  
7 acute and wherein the angles  $\alpha$  and  $\beta$  form first and second planes respectively which are  
8 orthogonal with respect to each other; and

9           the angle  $\beta$  is being  $30^\circ$  and the angle  $\alpha$  is being  $40^\circ$ .

F<sub>1</sub>  
Cont'd  
2  
3  
59. (Original) A method as claimed in claim 55 wherein said at least one material  
layer is a nickel iron film and first and second cobalt based films with the nickel iron layer being  
located between the first and second cobalt based films for forming said magnetic layer.

1           60. (Currently Amended) ~~A method as claimed in claim 59 wherein~~ A method of  
2 making a magnetic layer and/or an antiferromagnetic (AFM) layer for an electrical device  
3 comprising the steps of:

4           obliquely ion beam sputtering at least one material layer from a target onto a substrate to  
5 form said magnetic layer and/or antiferromagnetic (AFM) layer;

6           the oblique ion beam sputtering being at angles  $\alpha$  and  $\beta$  wherein each angle  $\alpha$  and  $\beta$  is  
7 acute and wherein the angles  $\alpha$  and  $\beta$  form first and second planes respectively which are  
8 orthogonal with respect to each other;

9           said at least one material layer being a nickel iron film and first and second cobalt based  
10 films with the nickel iron layer being located between the first and second cobalt based films for  
11 forming said magnetic layer; and

12           a second material layer comprising a nickel oxide film and an  $\alpha$  phase iron oxide film that  
13 interface one another are being obliquely ion beam sputtered at said angles  $\alpha$  and  $\beta$  for forming  
14 said antiferromagnetic layer.

1           61. (Original) A method as claimed in claim 60 wherein for each of said magnetic  
2 and AFM layers the angle  $\beta$  is  $10^\circ$  to  $30^\circ$ .

1           62. (Original) A method as claimed in claim 61 wherein for said magnetic layer  
2 the angle  $\beta$  is  $20^\circ$  and the angle  $\alpha$  is  $40^\circ$ .



1           **63. (Original)**     A method as claimed in claim 55 wherein the electrical device is a  
2 magnetic head assembly and further comprises the steps of:  
3           said at least one material layer being a ferromagnetic free layer;  
4           a ferromagnetic pinned layer;  
5           a nonmagnetic spacer layer located between the free and pinned layers; and  
6           the pinned and spacer layers being ion beam sputtered at an angle  $\alpha$  which is acute and at  
7           an angle  $\beta$  which is zero.

41  
Control  
1           **64. (Currently Amended)**     ~~A method as claimed in claim 55 wherein the electrical~~  
2 ~~device is a magnetic head assembly and further comprises:~~ A method of making a magnetic layer  
3 and/or an antiferromagnetic (AFM) layer for an electrical device comprising the steps of:  
4           obliquely ion beam sputtering at least one material layer from a target onto a substrate to  
5 form said magnetic layer and/or antiferromagnetic (AFM) layer;  
6           the oblique ion beam sputtering being at angles  $\alpha$  and  $\beta$  wherein each angle  $\alpha$  and  $\beta$  is  
7 acute and wherein the angles  $\alpha$  and  $\beta$  form first and second planes respectively which are  
8 orthogonal with respect to each other;  
9           said at least one material layer being a ferromagnetic free layer;  
10          forming a ferromagnetic pinned layer;  
11          forming a nonmagnetic spacer layer between the free and pinned layers; and  
12          the pinned and spacer layers being ion beam sputtered at an angle  $\alpha$  which is acute and at  
13          an angle  $\beta$  which is 10° to 30°.

1           **65. (Original)**     A method as claimed in claim 64 wherein the free layer has a  
2 magnetic moment with an easy axis and the oblique sputtering of the free layer is done in the  
3 presence of a magnetic field oriented parallel to said easy axis.

1           **66. (Original)**     A method as claimed in claim 65 wherein after oblique sputtering  
2 the free layer the free layer is annealed at a temperature from 150°C to 270°C in the presence of  
3 said field oriented parallel to said easy axis.

1           **67. (Original)**     A method as claimed in claim 66 wherein for the free layer the angle  
2  $\beta$  is 20° and the angle  $\alpha$  is 40°.

1           **68. (Currently Amended)**     A method as claimed in claim 67 wherein for the pinned  
2 and spacer layers angle  $\alpha$  is 40° and angle  $\beta$  is 0°.

1           69.     (Original)     A method as claimed in claim 68 further including the steps of:  
2           forming said antiferromagnetic (AFM) layer interfacing the pinned layer wherein the AFM  
3           layer includes a nickel oxide film and an  $\alpha$  phase iron oxide film that interface one another; and  
4           ion beam sputtering the nickel oxide film and the  $\alpha$  phase iron oxide film at angles  $\alpha$  and  
5            $\beta$  wherein each angle  $\alpha$  and  $\beta$  are acute and wherein the angles  $\alpha$  and  $\beta$  form first and second  
6           planes respectively which are orthogonal with respect to one another.

1           70.     (Original)     A method as claimed in claim 69 wherein for the AFM layer the  
2           angle  $\alpha$  is  $40^\circ$  and angle  $\beta$  is  $10^\circ - 30^\circ$ .

1           71.     (Allowed)     A method as claimed in claim 32 wherein the forming of the spacer  
2           layer includes oblique ion beam sputtering copper at angles  $\alpha = 40^\circ$  and  $\beta = 10^\circ - 30^\circ$  with angles  
3            $\alpha$  and  $\beta$  being orthogonal.

1           72.     (Allowed)     A method as claimed in claim 41 wherein the forming of the spacer  
2           layer includes oblique ion beam sputtering copper at angles  $\alpha = 40^\circ$  and  $\beta = 10^\circ - 30^\circ$  with angles  
3            $\alpha$  and  $\beta$  being orthogonal.

1           73.     (Allowed)     A method as claimed in claim 48 wherein the forming of the spacer  
2           layer includes oblique ion beam sputtering copper at angles  $\alpha = 40^\circ$  and  $\beta = 10^\circ - 30^\circ$  with angles  
3            $\alpha$  and  $\beta$  being orthogonal.

1           74.     (Original)     A method of ion beam sputtering at least one layer comprising the  
2           steps of:  
3           providing a substrate with a first planar surface;  
4           providing at least one target with a second planar surface wherein the target is composed  
5           of a desired material for said layer;  
6           positioning the planar surfaces at angles  $\alpha$  and  $\beta$  with respect to one another wherein angle  
7            $\alpha$  forms a first plane intersecting the first and second planar surfaces and angle  $\beta$  forms a second  
8           plane intersecting the first and second planar surfaces as well as the first plane with the  
9           intersection of the first and second planes being orthogonal with respect to each other; and  
10          ion beam sputtering the target so that said material is sputtered from the target onto said  
11          substrate to form said layer.

1           75.     (Original)     A method as claimed in claim 74 wherein a central ion beam lies  
2           within said first plane.

1           76.   (Currently Amended)   ~~A method as claimed in claim 75 wherein~~ A method of  
2 ion beam sputtering at least one layer comprising the steps of:  
3           providing a substrate with a first planar surface;  
4           providing at least one target with a second planar surface wherein the target is composed  
5 of a desired material for said layer;  
6           positioning the planar surfaces at angles  $\alpha$  and  $\beta$  with respect to one another wherein angle  
7  $\alpha$  forms a first plane intersecting the first and second planar surfaces and angle  $\beta$  forms a second  
8 plane intersecting the first and second planar surfaces as well as the first plane with the  
9 intersection of the first and second planes being orthogonal with respect to each other; and  
10          ion beam sputtering the target so that said material is sputtered from the target onto said  
11 substrate to form said layer;  
12          a central ion beam lying within said first plane; and  
13          the angle  $\beta$  is being  $10^\circ$  to  $30^\circ$ .

1           77.   (Currently Amended)   ~~A method as claimed in claim 75 wherein~~ A method of  
2 ion beam sputtering at least one layer comprising the steps of:  
3           providing a substrate with a first planar surface;  
4           providing at least one target with a second planar surface wherein the target is composed  
5 of a desired material for said layer;  
6           positioning the planar surfaces at angles  $\alpha$  and  $\beta$  with respect to one another wherein angle  
7  $\alpha$  forms a first plane intersecting the first and second planar surfaces and angle  $\beta$  forms a second  
8 plane intersecting the first and second planar surfaces as well as the first plane with the  
9 intersection of the first and second planes being orthogonal with respect to each other; and  
10          ion beam sputtering the target so that said material is sputtered from the target onto said  
11 substrate to form said layer;  
12          a central ion beam lying within said first plane; and  
13          the angle  $\beta$  is being  $20^\circ$  and the angle  $\alpha$  is being  $40^\circ$ .

1           78.   (Currently Amended)   ~~A method as claimed in claim 75 wherein~~ A method of  
2 ion beam sputtering at least one layer comprising the steps of:  
3           providing a substrate with a first planar surface;  
4           providing at least one target with a second planar surface wherein the target is composed  
5 of a desired material for said layer;  
6           positioning the planar surfaces at angles  $\alpha$  and  $\beta$  with respect to one another wherein angle  
7  $\alpha$  forms a first plane intersecting the first and second planar surfaces and angle  $\beta$  forms a second  
8 plane intersecting the first and second planar surfaces as well as the first plane with the  
9 intersection of the first and second planes being orthogonal with respect to each other; and

10 ion beam sputtering the target so that said material is sputtered from the target onto said  
11 substrate to form said layer;

12 a central ion beam lying within said first plane; and  
13 the angle  $\beta$  is being  $30^\circ$  and the angle  $\alpha$  is being  $40^\circ$ .

1 79. (Original) A method as claimed in claim 75 wherein said at least one layer is  
2 a nickel iron film and first and second cobalt based films with the nickel iron film being located  
3 between the first and second cobalt based films for forming said layer.

1 80. (Currently Amended) ~~A method as claimed in claim 79 wherein~~ A method of ion  
2 beam sputtering at least one layer comprising the steps of:  
3 providing a substrate with a first planar surface;  
4 providing at least one target with a second planar surface wherein the target is composed  
5 of a desired material for said layer;

6 positioning the planar surfaces at angles  $\alpha$  and  $\beta$  with respect to one another wherein angle  
7  $\alpha$  forms a first plane intersecting the first and second planar surfaces and angle  $\beta$  forms a second  
8 plane intersecting the first and second planar surfaces as well as the first plane with the  
9 intersection of the first and second planes being orthogonal with respect to each other; and

10 ion beam sputtering the target so that said material is sputtered from the target onto said  
11 substrate to form said layer;

12 a central ion beam lying within said first plane;

13 said at least one layer being a nickel iron film and first and second cobalt based films with  
14 the nickel iron film being located between the first and second cobalt based films for forming said  
15 layer; and

16 a second layer comprising a nickel oxide film and an  $\alpha$  phase iron oxide film that interface  
17 one another are being obliquely ion beam sputtered at said angles  $\alpha$  and  $\beta$  for forming another  
18 layer.

1 81. (Original) A method as claimed in claim 80 wherein for each of said layer and  
2 said other layer the angle  $\beta$  is  $10^\circ$  to  $30^\circ$ .

1 82. (Original) A method as claimed in claim 81 wherein for said layer the angle  
2  $\beta$  is  $20^\circ$  and the angle  $\alpha$  is  $40^\circ$ .

1           **83.**   (Original)   A method as claimed in claim 75 wherein said method forms a  
2 magnetic head assembly further comprising:  
3           said at least one layer being a ferromagnetic free layer;  
4           forming a ferromagnetic pinned layer;  
5           forming a nonmagnetic spacer layer between the free and pinned layers; and  
6           the pinned and spacer layers being ion beam sputtered at an angle  $\alpha$  which is acute and at  
7           an angle  $\beta$  which is zero.

1           **84.**   (Original)   A method as claimed in claim 83 wherein for the free layer the angle  
2            $\beta$  is 10° to 30°.

1           **85.**   (Original)   A method as claimed in claim 84 wherein the free layer has a  
2           magnetic moment with an easy axis and the oblique sputtering of the free layer is done in the  
3           presence of a magnetic field oriented parallel to said easy axis.

1           **86.**   (Original)   A method as claimed in claim 85 wherein after oblique sputtering  
2           the free layer the free layer is annealed at a temperature from 150°C to 270°C in the presence of  
3           said field oriented parallel to said easy axis.

1           **87.**   (Original)   A method as claimed in claim 86 wherein for the free layer the angle  
2            $\beta$  is 20° and the angle  $\alpha$  is 40°.

1           **88.**   (Original)   A method as claimed in claim 87 wherein for the pinned and spacer  
2           layers angle  $\alpha$  is 40° and angle  $\beta$  is 0°.

1           **89.**   (Original)   A method as claimed in claim 88 further comprising:  
2           forming an antiferromagnetic (AFM) layer interfacing the pinned layer wherein the AFM  
3           layer includes a nickel oxide film and an  $\alpha$  phase iron oxide film that interface one another; and  
4           ion beam sputtering the nickel oxide film and the  $\alpha$  phase iron oxide film at angles  $\alpha$  and  
5            $\beta$  wherein each angle  $\alpha$  and  $\beta$  are acute and wherein the angles  $\alpha$  and  $\beta$  form first and second  
6           planes respectively which are orthogonal with respect to one another.

1           **90.**   (Original)   A method as claimed in claim 89 wherein for the AFM layer the  
2           angle  $\alpha$  is 40° and angle  $\beta$  is 10° - 30°.

**Add new claims 91-93.**

1 91. (New) A method as claimed in claim 55 wherein each of angles  $\alpha$  and  $\beta$  is greater  
2 than zero.

*F<sub>1</sub> 1*  
*Cont'd* 92. (New) A method as claimed in claim 74 wherein each of angles  $\alpha$  and  $\beta$  is greater  
1 than zero.

1 93. (New) A method as claimed in claim 83 wherein each of angles  $\alpha$  and  $\beta$  is greater  
2 than zero.

---